



Sieve Analysis Report

CLIENT:	Metro Green	DATE:	2/9/2026
PROJECT:	YARD STOCK PILE	LAB NO:	20812
SAMPLE ID:	3/4" - 1" Recycled Gravel	TIME IN:	8am
RECEIVED:		TIME OUT:	3pm
INSPECTOR:	Dale Joseph		

Sieve Size	Grain Size (mm)	Grams		RESULTS	
		Weight Retained	% Retained	Cumulative % Retained	% Passing
1"	25.4	224.4	19.84	19.84	80.16
3/4"	19.05	698	61.7	81.54	18.46
1/2"	12.7	204.0	18.03	99.57	0.43
3/8"	9.525	0	0	99.57	0.43
#4 - 1/4"	4.75	0	0	99.57	0.43
#10 - 1/10"	2.45	0	0	99.57	0.43
#60 - 1/60"	0.423	1.0	.09	99.66	0.34
#100 - 1/100"	0.254	0.7	.06	99.72	0.28
#200 - 1/200"	0.127	0.7	.06	99.78	0.22
Pan		2.4	.22	100	0

Wet Soil (Ws): 1191.2

Dry Soil (Ds): 1131.2

Moisture Content: 5.04%

RESULTS:	<ol style="list-style-type: none"> 1. CONTAINS LESS THAN 5% FINES AND FINE MATERIAL. 2. MATERIAL CONFORMS TO THE REQUIREMENTS OF SECTION 304 OF NYS DOT S.S. FOR TYPE 4 MATERIAL.
-----------------	---

EQUIPMENT USED:	Sieves; SN: CTL-SIV003 / CTLSIV038 Shaker, SN: -CTMSS002; Scale SN: CTL-SCL-003
------------------------	--

Respectfully submitted,
CERTIFIED TESTING LABORATORIES, INC

VS/dk

Vladimir Sirota, PE



CTL SOF S-3

